

July 25, 2011

TABLE I ANALYSIS RESULTS

CRIQ No.	FINES (%)	DIAMETER (mm)	LENGTH GREATER THAN 1,50 INCHES (%)	MOISTURE (%)	BULK DENSITY (lb./cubic foot)	« PELLET DURABILITY INDEX » (PDI)	CHLORIDE (ppm)	ASH (%)	HEATING VALUE (Dry Basis)		
									Btu/lb	MJ/kg	KWh/kg
44473	0.5	6.66	0.26	4.4	42.4	98.4	110	0.4	8 280	19.26	5.35